



# Titacon GF915

樹 酯 Resin : Polyacetal resin (POM)

產品說明 Product description : 15% 玻璃纖維、高強度

15% Glass Fiber 、High Strength

| 項目<br>Properties                                     | 單位<br>Unit        | 測試方法<br>Method                                    | 數值<br>Value                        |
|------------------------------------------------------|-------------------|---------------------------------------------------|------------------------------------|
| 顏色 Color                                             | -                 | -                                                 | Natural                            |
| 比重 Specific gravity                                  | g/cm <sup>3</sup> | ISO 1183                                          | 1.51                               |
| 拉伸強度 Tensile strength                                | MPa               | ISO 527-1,2                                       | 105                                |
| 拉伸率 Tensile Elongation                               | %                 |                                                   | 3                                  |
| 彎曲強度 Flexural strength                               | MPa               | ISO 178                                           | 150                                |
| 彎曲模數 Flexural modulus                                |                   |                                                   | 5200                               |
| 衝擊強度(有缺口)<br>Charpy impact strength(notched)         | kJ/m <sup>2</sup> | ISO 179                                           | 6                                  |
| 熱變形溫度(1.8MPa)<br>Heat Deflection Temperature(1.8MPa) | °C                | ISO 75-1,2                                        | 153                                |
| 體積阻抗 Volume resistivity                              | Ω•cm              | IEC 60093                                         | 1×10 <sup>14</sup>                 |
| 表面阻抗 Surface resistivity                             | Ω                 |                                                   | 1×10 <sup>15</sup>                 |
| 耐燃性 Flammability                                     |                   | UL 94                                             | HB                                 |
| 模收縮 Mold shrinkage                                   | %                 | 50x70x3<br>mmt                                    | 0.8~1.2                            |
| 成型條件<br>Molding condition                            | °C                | 乾燥條件 Drying<br>料管溫度 Melt temp.<br>模具溫度 Mold temp. | 90-110 x 4Hrs<br>170~200<br>60~100 |
|                                                      | %                 | 射出壓力 Inject. press.<br>射出速度 Inject. velocity      | 30~70<br>20~50                     |

以上數值為材料的代表性測試值、並非該規格材料的最低值。

All property values shown in this data sheet are the representative values and not minimum value of this material.