



## Titalon 4315TF

樹 酯 Resin : Polyamide 46 resin (PA46)

產品說明 Product description : 玻璃纖維/PTFE、高強度、耐磨耗

Glass Fiber/PTFE、High Strength、Wear Resistance

| 項目<br>Properties                                     | 單位<br>Unit        | 測試方法<br>Method        | 數值<br>Value        |
|------------------------------------------------------|-------------------|-----------------------|--------------------|
| 顏色 Color                                             | -                 | -                     | Natural            |
| 比重 Specific gravity                                  | g/cm <sup>3</sup> | ISO 1183              | 1.40               |
| 拉伸強度 Tensile strength                                | MPa               | ISO                   | 170                |
| 拉伸率 Tensile Elongation                               | %                 | 527-1,2               | 2                  |
| 彎曲強度 Flexural strength                               | MPa               | ISO 178               | 235                |
| 彎曲模數 Flexural modulus                                |                   |                       | 8000               |
| 衝擊強度(有缺口)<br>Charpy impact strength(notched)         | kJ/m <sup>2</sup> | ISO<br>179/1eA        | 10                 |
| 熱變形溫度(1.8MPa)<br>Heat Deflection Temperature(1.8MPa) | °C                | ISO<br>75-1,2         | 280                |
| 體積阻抗 Volume resistivity                              | Ω•cm              | IEC 60093             | 1×10 <sup>13</sup> |
| 表面阻抗 Surface resistivity                             | Ω                 |                       | 1×10 <sup>14</sup> |
| 耐燃性 Flammability                                     |                   | UL 94                 | HB                 |
| 模收縮 Mold shrinkage                                   | %                 | 50x70x3<br>mmt        | 0.3~0.7            |
| 成型條件<br>Molding condition                            | °C                | 乾燥條件 Drying           | 100 x 4Hrs         |
|                                                      |                   | 料管溫度 Melt temp.       | 290~320            |
|                                                      |                   | 模具溫度 Mold temp.       | 80~120             |
|                                                      | %                 | 射出壓力 Inject. press.   | 30~70              |
|                                                      |                   | 射出速度 Inject. velocity | 30~60              |

\*以上數值為材料的代表性測試值、並非該規格材料的最低值。

\*All property values shown in this data sheet are the representative values and not minimum value of this material.